

Grille 2.0 VINYL SEATING

## Performance Summary

- · Enhanced soil + stain resistance
- Enhanced abrasion resistance
- · CFFA-Healthcare-201: Certified
- · Enhanced ink resistance
- · Denim dye resistant
- · Fluid barrier
- · Bleach-solution cleanable
- · Enhanced fade resistance
- · Indoor / Outdoor

## Environmental

- · GREENGUARD Certified
- REACH Compliant
- RoHS Compliant
- No fluorocarbons or perfluorinated compounds
- · No added flame retardants
- · No added antimicrobials
- · Does not contain formaldehyde

## Cleaning and Maintenance

Cleaning Code: (W-S) For water-based stains use water-based cleaners. For oil-based stains use solvent-based cleaners. We recommend using a professional cleaning service.

Bleach solutions of up to 10% may be used for more difficult stains.

Dye lots may vary slightly.

- \* This term and any corresponding data refer to the typical performance in the tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.
- \*\* Multiple factors affect fabric durability and appearance retention, including end-user application and proper maintenance. Wyzenbeek results above 100,000 double rubs have not been shown to be an indicator of increased lifespan.

Specifications	<b>##</b> ★□
Content	Vinyl Surface with Polyester Backing
Finish	Advanced Soil and Stain Resistant Top Coat + ink resistance
Backing	Polyester
Weight	30.0 oz./lin. yd. ± 1.0 oz.
Width	54 inches
Roll Size	30 yards
Performance Characteristics	
Abrasion Resistance** ASTM D-4157	Exceeds 100,000 double rubs - heavy duty
Adhesion ASTM D-751	Warp: 3.3 lbs. min., Fill: 3.3 lbs. min.
Break Strength ASTM D-751-89	Warp: 121 lbs. min., Fill: 72 lbs. min.
Tear Strength CFFA-16	Warp: 18 lbs. min., Fill: 18 lbs. min.
Colorfastness to Light AATCC-16	1000 Hours, Class 4.5
Crocking AATCC-8	Dry: Class 5.0, Wet: Class 5.0
Fluid Barrier	Inherent Fluid Barrier
Flammability*	A SECTION AND AN AND AND
California Technical Bulletin 117-2013 Section 1	Passed
UFAC	Class 1
NFPA 260	Class 1
	WAS A STATE OF THE

